

AC210 Hand Length

2.1 Mil Premium Acrylic CST

DESCRIPTION

Durable biaxially-oriented polypropylene (BOPP) film coated with high grade pressure-sensitive emulsion acrylic adhesive.

Best suited for reliable, all-temperature box sealing performance (less than 40°F and greater than 120°F) where resistance to aging, weathering, UV light, and yellowing are important. Provides excellent clarity, long life in use, superior quick-stick performance, and controlled unwind to facilitate dispensing on manual or automatic case sealing machines.

PRODUCT APPLICATION

Medium weight box sealing and other packaging applications exposed to normal shipping hazards and stress.

GOVERNMENT COMPLIANCE

Complies with the Federal Food Drug and Cosmetic Act, CFR Title 21, Subpart B, Par 175.105, which covers the use of pressure sensitive adhesives and tapes for indirect contact food packaging, such as box sealing.

TUFFlex™

tufflexpackaging.com

1 844-VERITIV

1000 Abernathy Rd. NE, Bldg. 400,
Suite 1700, Atlanta, GA 30328, USA

© 2020 Veritiv Corporation. All rights reserved. TUFFlex is a trademark of Veritiv Corporation or its affiliates. While we believe them to be reliable, the statements and information herein are only for general guidance and are not warrants or guarantees for accuracy and completeness. The user must, by test or otherwise, determine suitability for this purpose. There is no warranty of fitness for a particular purpose. Our standard terms and conditions of sale apply exclusively to all orders and all liability for damages of any kind, including consequential, exceeding purchase price is excluded. No one is authorized by us to make oral warranties. We reserve the right to make changes without notice or obligation in our products and publications. WF350844

NOMINAL VALUES

The following data are nominal values based on PSTC, ASTM and other standard tests. The data should not be considered as specifications.

BACKING	1.1 mil (0.028 mm)
ADHESIVE	Emulsion Acrylic
ELONGATION (% at break) ASTM D3759	> 100
ADHESION TO STEEL ASTM D3330	> 190 g/cm (17 oz/in)
TOTAL THICKNESS ASTM D3652	2.1 mil (0.053 mm)
OPERATING TEMPERATURE RANGE	Application +32°F to +150°F (0°C ~ +65°C)
	Operating -30°F to +200°F (-35°C ~ +93°C)
COLOUR	Clear