

HM170 Hand Length

1.7 Mil Premium Hot Melt CST

DESCRIPTION

Cold temperature biaxially-oriented polypropylene (BOPP) film carton sealing tape with specially designed pressure-sensitive hot melt adhesive offers a safe and attractive seal in cold, damp environments.

Excellent processing performance whether manually or automatically applied. Superior adhesion properties, holding force, tensile strength, and easy unwind ensure consistent, reliable seals to a variety of corrugated and linerboard boxes.

PRODUCT APPLICATION

For light to medium weight, manual box sealing applications at room temperature as well as cooler food packaging and processing applications and moving/storage applications.

GOVERNMENT COMPLIANCE

Complies with the Federal Food, Drug and Cosmetic Act, CFR Title 21, Subpart B, Par. 175.105 (covers the use of pressure-sensitive adhesives and tapes for 'indirect contact' food packaging, such as box sealing). CID A-A-1684B.

TUFFflex™

tuffflexpackaging.com

1 844-VERITIV

1000 Abernathy Rd. NE, Bldg. 400,
Suite 1700, Atlanta, GA 30328, USA

© 2019 Veritiv Corporation. All rights reserved. TUFFflex is a trademark of Veritiv Corporation or its affiliates. While we believe them to be reliable, the statements and information herein are only for general guidance and are not warrants or guarantees for accuracy and completeness. The user must, by test or otherwise, determine suitability for this purpose. There is no warranty of fitness for a particular purpose. Our standard terms and conditions of sale apply exclusively to all orders and all liability for damages of any kind, including consequential, exceeding purchase price is excluded. No one is authorized by us to make oral warranties. We reserve the right to make changes without notice or obligation in our products and publications. WF237768

NOMINAL VALUES

The following data are nominal values based on PSTC, ASTM and other standard tests. This data should not be considered specification.

BACKING (Blown Film)	1.0 mil (0.025 mm)
ADHESIVE	Synthetic Rubber/Resin
TENSILE STRENGTH (lbs/in of width) ASTM D3759	25 (438 N/100 mm)
ELONGATION (% at break) ASTM D3759	80
ADHESION TO STEEL (oz/in of width) ASTM D3330	25 (27.4 N/100 mm)
SHEAR TO LINERBOARD (1/2" x 1/2" x 1000 grams) ASTM D3654	2500+ minutes
TOTAL THICKNESS ASTM D3652	1.70 mil (0.043 mm)
OPERATING TEMPERATURE RANGE	Application +35°F to +120°F (+1.7°C ~ +49°C) Operating -40°F to 140°F (-40°C ~ +60°C)
COLOUR	Clear

HM170 Machine Length

1.7 Mil Premium Hot Melt CST

DESCRIPTION

Cold temperature biaxially-oriented polypropylene (BOPP) film carton sealing tape with specially designed pressure-sensitive hot melt adhesive offers a safe and attractive seal in cold, damp environments.

Excellent processing performance whether manually or automatically applied. Superior adhesion properties, holding force, tensile strength, and easy unwind ensure consistent, reliable seals to a variety of corrugated and linerboard boxes.

PRODUCT APPLICATION

For light to medium weight, manual box sealing applications at room temperature as well as cooler food packaging and processing applications and moving/storage applications.

GOVERNMENT COMPLIANCE

Complies with the Federal Food, Drug and Cosmetic Act, CFR Title 21, Subpart B, Par. 175.105 (covers the use of pressure-sensitive adhesives and tapes for 'indirect contact' food packaging, such as box sealing). CID A-A-1684B.

TUFFflex™

tuffflexpackaging.com

1 844-VERITIV

1000 Abernathy Rd. NE, Bldg. 400,
Suite 1700, Atlanta, GA 30328, USA

© 2019 Veritiv Corporation. All rights reserved. TUFFflex is a trademark of Veritiv Corporation or its affiliates. While we believe them to be reliable, the statements and information herein are only for general guidance and are not warrants or guarantees for accuracy and completeness. The user must, by test or otherwise, determine suitability for this purpose. There is no warranty of fitness for a particular purpose. Our standard terms and conditions of sale apply exclusively to all orders and all liability for damages of any kind, including consequential, exceeding purchase price is excluded. No one is authorized by us to make oral warranties. We reserve the right to make changes without notice or obligation in our products and publications. WF237768

NOMINAL VALUES

The following data are nominal values based on PSTC, ASTM and other standard tests. This data should not be considered specification.

BACKING (Blown Film)	1.0 mil (0.025 mm)
ADHESIVE	Synthetic Rubber/Resin
TENSILE STRENGTH (lbs/in of width) ASTM D3759	19 (333 N/100 mm)
ELONGATION (% at break) ASTM D3759	125
ADHESION TO STEEL (oz/in of width) ASTM D3330	25 (27.4 N/100 mm)
SHEAR TO LINERBOARD (1/2" x 1/2" x 1000 grams) ASTM D3654	2500+ minutes
TOTAL THICKNESS ASTM D3652	1.70 mil (0.043 mm)
OPERATING TEMPERATURE RANGE	Application +35°F to +120°F (+1.7°C ~ +49°C) Operating -40°F to 140°F (-40°C ~ +60°C)
COLOUR	Clear