

V02445

TUFFlex Ultra Película de Máquina

10.7 Micrones / 42 Calibre / 0.42 Mil

No deben considerarse como especificaciones limitantes

CARACTERISTICAS

VALORES

Proceso de fabricación	Fundido
Espesor (nominal)	10.7 Micrones / 42 Calibre / 0.42 Mil
Color	Transparente
Ancho de Película (pulgadas)	20"
Largo (pies)	11,000'
Peso Neto/Rollo (lbs-nominal)	36.96 lbs
Diámetro de Rollo (D.E, pulgadas)	9.5"
Tubo D.I.	3"

PRUEBAS

METODOS

VALORES

Opacidad	ASTM D1003	3.0%
Brillo	ASTM D2457	69%
Resistencia al Impacto por Dardo	ASTM D1709	175 g
Resistencia a la Tensión a la Rotura (DM)	ASTM D882	5500 psi
Resistencia a la Tensión a la Rotura (DT)	ASTM D882	4575 psi
Resistencia a la Tensión, al 200% (DM)	ASTM D882	1960 psi
Resistencia a la Tensión, al 200% (DT)	ASTM D882	1425 psi
Estiramiento a la Rotura (DM)	ASTM D882	495%
Estiramiento a la Rotura (DT)	ASTM D882	645%
Resistencia al desgarre Elmendorf (DM)	ASTM D1922	135 g
Resistencia al desgarre Elmendorf (DT)	ASTM D1922	365 g
Adherencia	ASTM D5458	100 g

tufflexpackaging.com

844-VERITIV

1000 Abernathy Rd NE | Building 400 | Suite 1700 | Atlanta, GA 30328 | USA

© 2017 Veritiv Corporation. Todos los derechos reservados. TUFFflex es una marca registrada de Veritiv Corporation o de sus afiliados.

V02445

TUFFlex Ultra Machine Film

10.7 Micron / 42 Gauge / 0.42 Mil

Not intended as limiting specifications

CHARACTERISTICS

CHARACTERISTICS	VALUES
Manufacturing Process	Cast
Thickness (nominal)	10.7 Micron / 42 Gauge / 0.42 Mil
Color	Clear
Film Width (inches)	20"
Length (feet)	11,000'
Net Weight/Roll (lbs–nominal)	36.96 lbs
Roll Diameter (O.D., inches)	9.5"
Core I.D.	3"

TESTS

TESTS	METHODS	VALUES
Haze	ASTM D1003	3.0%
Gloss	ASTM D2457	69%
Dart Impact Strength	ASTM D1709	175 g
Tensile Strength at Break (MD)	ASTM D882	5500 psi
Tensile Strength at Break (TD)	ASTM D882	4575 psi
Tensile Strength at 200% (MD)	ASTM D882	1960 psi
Tensile Strength at 200% (TD)	ASTM D882	1425 psi
Elongation at Break (MD)	ASTM D882	495%
Elongation at Break (TD)	ASTM D882	645%
Elemdorf Tear Strength (MD)	ASTM D1922	135 g
Elemdorf Tear Strength (TD)	ASTM D1922	365 g
Cling	ASTM D5458	100 g

tufflexpackaging.com

844-VERITIV

1000 Abernathy Rd NE | Building 400 | Suite 1700 | Atlanta, GA 30328 | USA

© 2017 Veritiv Corporation. All rights reserved. TUFFlex is a registered trademark of Veritiv Corporation or its affiliates.

Ref: 86500 April 2017 TFTDSV02445MX

TUFFlex™